

## REFLEXFIM

standard SRPS U.M3.240

### PRODUCT DESCRIPTION:

Cold bituminous liquid spread bitumen and organic solvents

### FIELDS OF APPLICATION:

REFLEXFIM is used under the cold procedure for protection of flat roofs waterproofing from UV radiation emanating from the sun.

### CHEMICAL COMPOSITION:

REFLEXFIM is an unicomponent protective paint composed of aluminium pigment, bitumen, polymeric additive and organic solvent.

### PRODUCT CHARACTERISTICS:

GENERAL FEATURES		
Aspect		Homogenous paste
Colour		Metallic grey
Binder content	%	min. 40
Solvent content	°C	min. 70
Point of inflammability acc. to Markuson	°C	max. 35
Flow resistance at elevated temperature, no leakage	°C	80
Flexibility at low temperature, no cracking	°C	0
Time of drying	min	60

### USAGE:

It should be put on dry, solid and clean substrate with brush, roller in two layers. Before using must be mixed till homogeneous state. The drying period depends on the external temperature and may vary from 1 - 4 hours. The recovery of the protective paint should be done in every 2 - 4 years. The average consumption, if it is used in two layers, is 0,5 kg/m<sup>2</sup>.

### PACKAGING, DELIVERY AND TRANSPORTATION:

REFLEXFIM is delivered in packaging of 12 and 23 kg. As highly inflammable material it is stored and transported in covered areas and vehicles, protected from the sun, heat and mechanical damages.

Our products are made according to standard ISO 9001 and ISO 14001

