

FABRIKA IZOLACIONIH MATERIJALA d.o.o.

Put Narodnih Heroja 12., 24420 KANJIŽA, SRB

Tel. +381 24 874-700 Fax +381 24 875-165

www.fim.co.rs e-mail: office@fim.co.rs



Topizol

standard SRPS U.M3.244

PRODUCT DESCRIPTION:

Bitumen based product for waterproofing under the hot procedure

FIELDS OF APPLICATION:

TOPIZOL is applied in hot condition for manufacturing of underground and aboveground waterproofing.

CHEMICAL COMPOSITION:

Bitumen, inert material.

PRODUCT CHARACTERISTICS:

GENERAL FEATURES		
Aspect		Solid material
Colour		Black
Bitumen content	%	min. 60
Filler content	%	max. 40
Softening point acc. to R&B	°C	min. 75
Precipitation in hot condition at 180°C	%	max. 5
Flow resistance at elevated temperature, no leakage	°C	70
Flexibility at low temperature, no cracking	°C	0
Watertightness	0,2 bar/8 h	Watertight

USAGE:

Melting of minced pieces should be made gradually accompanied by continuous mixing, the highest temperature not exceeding 180° C. When applying put it on the substrate previously treated by primer (FIMIZOL-EXPRESS) or on the membrane for waterproofing, with brush or by soakage, on which the following membrane is immediately being affixed. The average consumption is 2-3 kg/m².

PACKAGING, DELIVERY AND TRANSPORTATION:

TOPIZOL is delivered in solid state in tin packaging of 25 and 200 kg. It is correctly stored in covered area, upright, protected from the sun and heat.

Our products are made according to standard ISO 9001 and ISO 14001

